



DRAWINGS FOR ILLUSTRATIVE PURPOSES ONLY

TeXtroflash™ Flashing

- 40 mil thick composite membrane. Polyethylene sheeting factory-laminated to proprietary adhesive.
- Adhesive-backed with removable release paper.
- Provides dual-layered waterproofing protection.
- Self-seals around shafts on fasteners.
- Corners easily formed on site. Laps easily, just press at overlap.
- Resists tearing and slicing.
- UV-resistant for up to 90 days.

TeXtroflash™ Flashing may be used in thru-wall or surface-mount applications.

Width (rolls are 75 ft. long)

- 12" 20"
 16" 24"
 18" 36"

St/Steel Drip Plate (required for surface-mount application)

- 1 1/2" 3" Other _____

St/Steel Termination Bar (required for surface-mount application)

- T1 Termination Bar
 T2 Termination Bar

- H&B 1-Quart Mastic Tube
 H&B Primer 36 (5 gal. pail)
 H&B Mastic (5 gal. pail)

TeXtroflash™ Technical Data

Grab Tensile	Warp 240lb 1110 N	Weft 250lb 1110 N	ASTM D 5034-95
Tongue Tear	Warp 58lb 258 N	Weft 60lb 266 N	ASTM D 2261-96
Trapezoidal Tear	Warp 42lb 186 N	Weft 45lb 1110 N	ASTM D 4533-04
Mullen Burst	500 psi 3449 kPa		ASTM D 3786-01
Accelerated UV Weathering	>90% strength retention after 2000 hrs exposure @ 0.77 W/m ² /nm, or 1200 hrs exposure @ 1.35 W/m ² /nm		ASTM G 151-00 ASTM G 154-04